







Document No.: TQJ-91230 Date: 30-Dec-2009

### **NITTO DENKO (TAIWAN) CORPORATION**


Quality Assurance Dept.

Created By: Jeff Hsiao Approved By: Yu-Duan Chen NO.1 SOUTH 7TH RD. K.E.P.Z. KAOHSIUNG, TAIWAN. TEL 886-7-821-3106 $\sim$ 9 FAX 886-7-821-0677

# Vinyl adhesive tape No.223S(7.5mil)

\_\_\_\_ ビニル粘着テープ No.223S(7.5mil)

### 1. Constitution 構成



## 2. Test method 試験方法

According to UL-510 & CSA C22.2 No.197 (UL-510 & CSA C22.2 No.197 に準じる。)

## 3. Standard size 標準サイズ

Thickness	Width	Length	*Color	
厚さ(mm)	幅 (mm)	長さ (m)	色	
0.190	19, 25, 30, 38	20	Black, White, Blue, Gray, Red, Green, Yellow 黒、白、青、灰、赤、緑、黄	

Except for other standards, please consult with us.

仕様以外は、相談させて頂きます。)

### 4. Characteristic 一般特性

Item 項目		Unit 単位	No.223S
Thickness 全厚		mm	0.193
	to steel	N/19mm	6.43
Adhesion strength	対ステンレス板	(gf/19mm)	(656)
引き剥がし粘着力	to backing	N/19mm	5.38
	対自背面	(gf/19mm)	(549)
	low speed	N/19mm	7.36
Unwinding force	低速(0.3M/min)	(gf/19mm)	(751)
巻戻レ力	high speed	N/19mm	14.54
	高速(30M/min)	(gf/19mm)	(1483)
Elongation 伸 <i>び</i>		%	276
Tensile strength		N/19mm	73.5
引張強さ		(kgf/19mm)	(7.5)
Volume resistivity		Ω cm	3.5 x 10 <sup>13</sup>
体積抵抗		$(\log \Omega \ cm)$	(13.542)
Breakdown voltage 破壞電圧		Kv	10.79
Flame retardant 難燃性			ОК
Heat resistant 耐熱性			ОК
Cold resistant 耐寒性			ОК

## Notice:

The data shown in this document are the examples of measured values but not for any specification purposes. Moreover, the data do not guarantee the conformity to the application(s) shown on this document. Please use this product after fully checking that there is no problem in conformity with adherent (the material which is applied by the tape)at your side. In addition, the intellectual property rights concerning this document belong to NITTO DENKO CORP. It is strictly prohibited to copy and duplicate this document without prior consent of NITTO DENKO CORP.

If you have any question concerning this document, please contact the sector in charge of this document.